

- 8 -

WHAT IS CLAIMED IS:

1. A polyhydroxy hydrogensulfated trimetallic nitride endohedral metallofullerene comprising a plurality of hydroxyl groups and a plurality of hydrogensulfate groups covalently bonded to a fullerene encapsulating a trimetallic nitride.
5
2. The polyhydroxy hydrogensulfated endohedral metallofullerene of claim 1, wherein the trimetallic nitride comprises a rare earth element and/or a group IIIB element.
10
3. The polyhydroxy hydrogensulfated endohedral metallofullerene of claim 1, wherein the trimetallic nitride comprises metals chosen from among the group consisting of Scandium, Yttrium, Lanthanum, Gadolinium, Holmium, Erbium, Thulium, and Ytterbium.
15
4. An endohedral metallofullerene of the formula:
 $A_{3-n}X_nN@C_m(-OH)_i(-OSO_3H)_j$; where A and X are metal atoms, $n=0-3$; m is an even number between about 60 and about 200; $1 < i < m-j$; $1 < j < m-i$.
20
5. The endohedral metallofullerene of claim 4, wherein, A and/or X are rare earth element and/or a group IIIB element.
6. The endohedral metallofullerene of claim 4, wherein A and/or X are chosen from among the group consisting of Scandium, Yttrium, Lanthanum,
25 Gadolinium, Holmium, Erbium, Thulium, and Ytterbium.
7. A method of hydroxylation and hydrogensulfation of trimetallic nitride endohedral metallofullerene comprising,
reacting a trimetallic nitride endohedral metallofullerene with NaOH and
30 TBAH in toluene;

- 9 -

contacting the reacted reacting a trimetallic nitride endohedral metallofullerene with water and hydrogen peroxide to produce a hydroxylated trimetallic nitride endohedral metallofullerene; and,

5 reacting the hydroxylated trimetallic nitride endohedral metallofullerene with fuming sulfuric to hydrogensulfate the hydroxylated trimetallic nitride endohedral metallofullerene.

8. A polyhydroxylated hydrogensulfated trimetallic nitride endohedral metallofullerene made by the method of claim 7.